


**Meas.Nr.** 68949      **Date** Tuesday, 15 October 2013 11:12 AM      **Personal Report No.:**  
**Material** Indigo (MTP + Apollo)      15min P6 cl 1 mm ZrO2 80 ml bowl      **M130265**  
**Description** dispersed in IPA + 2min ultrasonic bath LABORETTE 17

**Calculation** Fraunhofer      broad      **TradeOff** 1.000000e+003  
**Scans Fine** 100      **Scans Coarse** 100      **Channels** 102      **Beam Obscuration** 14.00 %  
**Meas. Range** 0.08 [µm] - 2000.00 [µm]      **Pump** 0      **Ultrasonics** 0

%	< µm
5	0.45
10	0.54
15	0.62
20	0.69
25	0.76
30	0.82
40	0.96
50	1.10
60	1.27
70	1.46
80	1.72
90	2.11
95	2.47
98	2.88
99	3.16

%	< µm
0.0	0.1
0.3	0.2
7.4	0.5
13.6	0.6
28.1	0.8
43.0	1.0
56.1	1.2
71.7	1.5
82.7	1.8
87.8	2.0
95.3	2.5
98.5	3.0
99.6	3.5
100.0	4.0
100.0	5.0



▲ 68949 dQ3(x)      — 68949 Q3(x)